


Uncoated steel

Data Sheet



October 2019. This literature supersedes all previous issues



XLERPLATE[®] steel

AS/NZS 3678 – 400

General description

A high strength structural steel with nominal yield strength of 400MPa.

Typical uses

- General fabrication
- Structural members
- Bridges
- Storage tanks

Features & benefits

- Guaranteed minimum strength levels
- Excellent weldability
- Excellent formability
- ACRS accreditation (ACRS Certificate No. 120802)
- ATIC10 accreditation

Warnings

- This material should be used in conjunction with the appropriate structural design and welding standards
- Maximum recommended temperature for hot forming is 620°C. If heated above 620°C, mechanical properties may deteriorate.

Australian standards

AS/NZS 3678: 2016
AS/NZS 1365: 1996
ISO 9001:2015 Quality System certified

Normal / optional supply conditions

	Normal	Optional
Thickness Range	10mm – 80mm	-
Availability	By enquiry only	-
Edge Condition	Trimmed	-
Tolerances	AS/NZS 1365: 1996	-
Ultrasonic Inspection	-	AS 1710: 2007
Surface Inspection	BlueScope	Third party
Certification	BlueScope	Third party endorsed

Optional supply conditions may be subject to dimensional restrictions

Chemical composition

Element	Guaranteed Maximum %
Carbon	0.22
Silicon	0.55
Manganese	1.70
Phosphorus	0.040
Sulfur	0.030
Chromium	0.25
Nickel	0.50
Copper	0.40
Molybdenum	0.35
Aluminium	0.10
Niobium**	0.060
Titanium	0.040
CEQ (IIW)	0.48

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

** Niobium + Vanadium + Titanium ≤ 0.15%

Mechanical properties

Tensile Properties (Transverse)		Thickness (mm)				
		10 ≤ t ≤ 12	12 < t ≤ 20	20 < t ≤ 32	32 < t ≤ 50	50 < t ≤ 80
Yield Strength (MPa)	Guaranteed Min	400	380	360	360	360
Tensile Strength (MPa)	Guaranteed Min	480	480	480	480	480
Elongation 5.65√S ₀ (%)	Guaranteed Min	18	18	18	18	18

Formability	Thickness (mm)	Longitudinal	Transverse
Recommended min inside Radius	t ≤ 10	3.0t	2.0t
	10 < t ≤ 20	3.75t	2.5t
	t > 20	Hot Forming	

This product is not suitable for hot forming above 620 °C.

Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994)	Not deemed combustible

steel.com.au

Please ensure you have the correct data sheet for this product as displayed at www.steel.com.au

1800 024 402

steeldirect@bluescopesteel.com

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. XLERPLATE®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.