



# XLERPLATE® steel

## AS/NZS 3678 – 250L0

### General description

A medium strength structural steel with nominal yield strength of 250Mpa and guaranteed impact properties at 0°C.

### Typical uses

- General fabrication
- Structural members
- Bridges
- Storage tanks

### Features & benefits

- Guaranteed minimum strength levels
- Excellent weldability
- Excellent formability
- ACRS accreditation (ACRS Certificate No. 120802)
- ATIC10 accreditation

### Warnings

- This material should be used in conjunction with the appropriate structural design and welding standards
- An untrimmed (mill) edge may contain surface discontinuities associated with the rolling process (refer to clause 8 of AS/NZS 3678). The plate supplied may include an amount outside of the nominal ordered width, in accordance with relevant Australian standards. The area of the supplied plate which is outside of the nominal (customer ordered) width must not be used. Customers are advised to remove an equal width from each side of the plate when trimming.

### Australian standards

AS/NZS 3678: 2016

AS/NZS 1365: 1996

ISO 9001:2015 Quality System certified

### Normal / optional supply conditions

	Normal	Optional
Thickness Range	5mm – 150mm	-
Availability	Plate is available in standard sizes	For sizes outside standard plate offer refer to XLERPLATE® steel size schedule 1
Edge Condition	Untrimmed (Mill Edge)*	Trimmed
Tolerances	AS/NZS 1365: 1996	-
Ultrasonic Inspection	-	AS 1710: 2007
Surface Inspection	BlueScope	Third party
Certification	BlueScope	Third party endorsed

Optional supply conditions may be subject to dimensional restrictions

\*Plates less than 8mm in thickness are supplied with trimmed edges

## Chemical composition

Element	Guaranteed Maximum%
Carbon	0.22
Silicon	0.5
Manganese	1.70
Phosphorus	0.040
Sulfur	0.030
Chromium	0.25
Nickel	0.30
Copper	0.40
Molybdenum	0.08
Aluminium	0.10
Niobium**	0.020
Titanium	0.040
CEQ (IIW)	0.44

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

## Mechanical properties

Tensile Properties (Transverse)		Thickness (mm)						
		5 ≤ t ≤ 8	8 < t ≤ 12	12 < t ≤ 20	20 < t ≤ 32	32 < t ≤ 50	50 < t ≤ 80	80 < t ≤ 150
Yield Strength (MPa)	Guaranteed Min	280	260	250	250	250	240	230
Tensile Strength (MPa)	Guaranteed Min	410	410	410	410	410	410	410
Elongation 5.65√S <sub>0</sub> (%)	Guaranteed Min	22	22	22	22	22	22	22

Charpy Impact Properties	Longitudinal on 10 X 10 mm test piece	Test Temperature (°C)	Absorbed Energy (joules)	
			Avg. of 3	Individual.
Guaranteed Min	250L0	0	27	20

Formability	Thickness (mm)	Longitudinal	Transverse
Recommended min inside Radius	t ≤ 6	1.5t	1.0t
	6 < t ≤ 10	2.25t	1.5t
	10 < t ≤ 20	3.0t	2.0t
	20 < t ≤ 50	6.0t	4.0t
	t > 50	Hot Forming	

This product is not suitable for hot forming above 620 °C.

## Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994)	Not deemed combustible

steel.com.au

Please ensure you have the correct data sheet for this product as displayed at [www.steel.com.au](http://www.steel.com.au)

1800 024 402

[steeldirect@bluescopesteel.com](mailto:steeldirect@bluescopesteel.com)

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. XLERPLATE®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.