



TRU-SPEC® coil plate steel AS/NZS 1594 – HA200

General description

- Hot-rolled structural product with a minimum yield strength of 200 MPa, good ductility and good weldability

Typical uses

- Structural members
- Roll forming applications
- Brake press forming applications
- General fabrications
- Galvanising applications

Features & benefits

- Guaranteed minimum strength levels
- Excellent weldability
- Excellent formability
- Excellent for galvanising applications

Warnings

- This material should be used in conjunction with the appropriate design and welding standards.
- An untrimmed edge (Mill Edge) may contain minor surface discontinuities as a result of the rolling process. It is recommended that customers satisfy themselves that the edge is suitable for the application.

Australian and International Standards

AS/NZS 1594:2002 (R2016)

AS/NZS 1365:1996 (R2016)

ISO 9001:2015 Quality System Certified

Supply conditions

	Normal	Optional
Thickness Range	3.0– 12 mm *	-
Width Range	750 – 1550 mm *	-
Length Range	1200 – 9000 mm *	-
Surface Finish	Hot Rolled	-
Edge Condition	Untrimmed (Mill Edge)	Trimmed
Tolerance	AS/NZS 1365:1996 (R2016)	-
Flatness	Class A	-
Certification	BlueScope – Analysis and Mechanical tests	-

* Not all thickness, width & length combinations are available

Optional supply conditions are subject to dimensional restrictions

Chemical composition

Element	Guaranteed maximum %
Carbon	0.15
Silicon	0.030*
Manganese	0.60
Phosphorus	0.030
Sulfur	0.030
Aluminium	0.10
CEQ (IIW)	0.29

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr+Mo+V)}{5} + \frac{(Cu+Ni)}{15}$$

* Value refers to the BlueScope internal standard, whereas the AS/NZS 1594:2002 (R2016) guaranteed maximum is 0.35%

Mechanical properties

Tensile Properties (Longitudinal)		Guaranteed value
Yield Strength (MPa)	Guaranteed Minimum	200
Tensile Strength (MPa)	Guaranteed Minimum	300
Elongation 80 mm (%)	Guaranteed Minimum	22% (≤ 3 mm), 26% (> 3 mm)
180° Bend (transverse)	Guaranteed Minimum	0t (≤ 3 mm), 1t (> 3 mm)

t = thickness of test piece

Weldability Group

WTIA Group
1

Refer to WTIA Technical Note 1 or AS/NZS 1554.1:2014

steel.com.au

To ensure you have the most current Data Sheet

1800 024 402

steeldirect@bluescopesteel.com

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. TRU-SPEC®, TRUSPEC®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited.

© 2020 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved