Uncoated steel

Datasheet

April 2019. This literature supersedes all previous issues





Hot rolled strip AS/NZS 1594 – HA250

General description

 Hot-rolled structural steel with a minimum yield strength of 250 MPa, good ductility and good weldability

Typical uses

- Structural members
- Roll forming applications
- Brake press forming applications
- General fabrications

Features & benefits

- Excellent weldability
- Good formability
- Excellent for galvanizing applications

Supply conditions

Warnings

- This material should be used in conjunction with the appropriate design and welding standards.
- An untrimmed edge (Mill Edge) may contain minor surface discontinuities as a result of the rolling process. It is recommended that customers satisfy themselves that the edge is suitable for the application.

Australian and International Standards AS/NZS 1594: 2002 AS/NZS 1365: 1996 ISO9001: 2015 Quality System Certified

| | Normal | Optional |
|-----------------|-----------------------|-----------------------------------|
| Thickness Range | 1.5 – 12.7 mm * | - |
| Width Range | 750 – 1550 mm * | - |
| Surface Finish | Hot Rolled | Pickled & Oiled (1.6 to 6mm only) |
| Edge Condition | Untrimmed (Mill Edge) | Trimmed |
| Tolerance | AS/NZS 1365: 1996 | - |
| Certification | BlueScope | - |

* Not all thickness & width combinations are available

Optional supply conditions are subject to dimensional restrictions

Chemical composition

| Element | Guaranteed maximum % |
|------------|----------------------|
| Carbon | 0.20 |
| Silicon | 0.03* |
| Manganese | 1.20 |
| Phosphorus | 0.040 |
| Sulphur | 0.030 |
| Aluminium | 0.10 |
| CEQ (IIW) | 0.39 |

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr+Mo+V)}{5} + \frac{(Cu+Ni)}{15}$$

* Value refers to the BlueScope internal standard, whereas the AS/NZS 1594 guaranteed maximum is 0.35%

Mechanical properties

| Tensile Properties (Longitudinal) | | |
|-----------------------------------|--------------------|-------------------------|
| Yield Strength (MPa) G | Guaranteed Minimum | 250 |
| Tensile Strength (MPa) G | Guaranteed Minimum | 350 |
| Elongation 80 mm (%) G | Guaranteed Minimum | 20% (<=3mm), 24% (>3mm) |
| 180° Bend (transverse) G | Guaranteed Minimum | 1t <=5mm, 2t >5mm |

t = thickness of test piece

Weldability Group

| WTIA Group | |
|------------|--|
| 3 | |

Refer to WTIA Technical Note 1 or AS/NZS 1554.1:2014

steel.com.au

To ensure you have the most current Data Sheet

1800 024 402 steeldirect@bluescopesteel.com

For more information contact Steel Direct





The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved