

ZINCALUME® steel and zinc-coated steel in high temperature and food contact applications

Introduction

BlueScope manufactures ZINCALUME® aluminium/zinc/magnesium alloy-coated steel and zinc-coated steel products with a variety of coatings and finishes to meet the needs of customers.

For the purpose of understanding the effects of elevated temperature application, these products can be classified into two groups being ZINCALUME® steel and zinc-coated steel.

This Technical Bulletin provides information relating to the use of ZINCALUME® steel and zinc-coated steel in high temperature and food contact applications.

In general, for applications involving elevated temperatures, depending on the structural requirements of the component and the temperatures involved, potential changes to the mechanical properties of the base steel, at temperature and subsequent to heating, should be considered.

ZINCALUME® steel

ZINCALUME® steel must not be exposed to temperatures in excess of 200°C.

ZINCALUME® steel is supplied with a clear acrylic coating with a thickness of 1-2µm. This acrylic coating is prone to degradation above 200°C and can generate fumes above 250°C.

These fumes may be associated with a heavy odour and discoloration of the metal surface.

Zinc-coated steel

Zinc-coated steel must not be exposed to temperatures in excess of 250°C.

At temperatures between 250°C and 300°C, Fe-Zn alloy growth occurs which appears as spots / blankets on the surface which obscures the spangle pattern.

Between 300°C and 350°C, there is fracturing and detachment of the zinc coating and embrittlement of the base steel.

Food contact application

ZINCALUME® steel should not be used in any applications in contact with food, although it is suitable as a catchment for rainwater harvesting.

The surface treatments used in ZINCALUME® steel and the zinc in zinc-coated steel can become soluble when in contact with food acids.

As such, containers manufactured from ZINCALUME® steel and zinc-coated steel must not be used to store food or beverages.

The use of ZINCALUME® steel (which is manufactured with a clear acrylic resin coating) in toasters and heaters is not recommended due to the temperature application issues outlined above.

Aluminium/zinc/magnesium alloy-coated steel without a resin coating may be suitable in these applications.

steel.com.au

To ensure you have the most current information

1800 800 789

steeldirect@bluescopesteel.com
For more information contact Steel Direct



The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements. BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin. ZINCALUME®, BlueScope and the BlueScope brand mark are registered trademarks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.